

Pan-Ty® Cable Ties – Polypropylene

specifications

Mechanical and chemical attributes of natural and weather resistant polypropylene cable ties shall provide superior resistance to chemical attack when exposed to various concentrations of salts, bases, and acids. In addition, polypropylene ties shall be buoyant in liquid applications and shall float to the surface where they can be seen and recovered.



technical information

Tensile @ yield @ 73°F (psi):	4,100 per ISO 527
Water absorption (24 hours):	0.1% per ASTM D570
Radiation resistance (Rads):	1x10 ⁶
Weathering life expectancy (years)/ UV resistance:	7 – 9 years – Weather Resistant (100) 1 year – Natural (109)
Max. continuous use temperature:	239°F (115°C) per UL 746B
Min. application use temperature:	-76°F (-60°C) per EN 50146
Heat deflection temperature @ 1.8 Mpa:	122°F (50°C) per ASTM D648 ISO 75 -1/-2
Chemical resistance:	
Salts	Excellent
Hydrocarbons (Gas, Oil, Lubricants)	Good
Chlorinated Hydrocarbons	Good
Acids	Excellent
Bases	Excellent
Acid Rain	Excellent
Impact resistance:	Very Good

key features and benefits

Polypropylene material	Resists chemical attack when exposed to salts, bases, and acids in various concentrations to help maintain cable tie performance in harsh conditions
Buoyancy	Cable tie will float to the surface of most liquids so the tie can easily be seen and removed
One-piece design with locking wedge	Provides low thread force for easy and reliable installation; improves productivity and reduces operator fatigue
Curved, tapered tip (on applicable sizes)	Threads easily into head; installs quickly for improved productivity
Distinct green color (natural ties)	Easy to identify for operators and/or inspectors to ensure the proper cable tie is used in the right application (indoor use)
Black color with ultraviolet inhibitor (weather resistant ties)	Allows ties to withstand exposure to sunlight; contributes to weathering life expectancy (7 – 9 years)

applications

Polypropylene cable ties are used to fasten wiring and hoses in the chemical process industry and related harsh environments. Ideal for applications that demand a cable

tie material that provides superior chemical resistance to salts, bases, and acids in various solutions and concentrations.

Polypropylene Cable Ties

Miniature Cross Section 11 Lbs. (49N) Min. Loop Tensile

Natural: PLT1M-M109

Weather resistant: PLT1M-M100

Intermediate Cross Section 18 Lbs. (80N) Min. Loop Tensile

Natural: PLT1.5I-M109

Weather resistant: PLT1.5I-M100

Standard Cross Section 30 Lbs. (133N) Min. Loop Tensile

Natural: PLT2S-M109,
PLT3S-M109,
PLT4S-M109

Weather resistant: PLT2S-M100,
PLT3S-M100,
PLT4S-M100

Light-Heavy Cross Section 50 Lbs. (222N) Min. Loop Tensile

Natural: PLT2H-TL109,
PLT3H-TL109,
PLT4H-TL109

Weather resistant: PLT2H-TL100,
PLT3H-TL100,
PLT4H-TL100

Recommended Installation Tools

Hand tools tool controlled tension and cut-off:

GTS-E, GTH-E,
GS2B-E, GS4H-E,
GS4EH-E

Hand tools installer controlled tension and cut-off:

STS2, STH2,
ST3EH

Pneumatic tools: PTS, PPTS,
PTH

Pan-Ty® Cable Ties – Polypropylene

ordering information

Natural Part Number	Weather Resistant Part Number	Length In. (mm)	Width In. (mm)	Thickness In. (mm)	Max. Bundle Dia. In. (mm)	Min. Loop Tensile Strength Lbs. (N)	Recommended Installation Tool	Bulk Pkg. Qty.*	Bulk Ctn. Qty.
Miniature Cross Section									
PLT1M-M109	PLT1M-M100	3.9 (99)	0.098 (2.5)	0.043 (1.1)	0.87 (22)	11 (49)	GTS-E, GS2B-E, PTS, PPTS, STS2	1000	50,000
Intermediate Cross Section									
PLT1.5I-M109	PLT1.5I-M100	5.6 (142)	0.142 (3.6)	0.045 (1.1)	1.38 (35)	18 (80)	GTS-E, GS2B-E, PTS, PPTS, STS2	1000	25,000
Standard Cross Section									
PLT2S-M109	PLT2S-M100	7.4 (188)	0.190 (4.8)	0.052 (1.3)	1.88 (48)	30 (133)	GTS-E, GS2B-E, GTH-E, GS4H-E, PTS, PTH, PPTS, STS2, STH2	1000	10,000
PLT3S-M109	PLT3S-M100	11.5 (292)			3.00 (76)			1000	10,000
PLT4S-M109	PLT4S-M100	14.5 (368)			4.00 (102)			1000	5,000
Light-Heavy Cross Section (Straight Tip)									
PLT2H-TL109	PLT2H-TL100	8.1 (206)	0.300 (7.6)	0.075 (1.9)	2.00 (51)	50 (222)	GTH-E, GS4H-E, GS4EH-E, PTH, STH2, ST3EH	250	2,500
PLT3H-TL109	PLT3H-TL100	11.4 (290)			3.00 (76)			250	2500
PLT4H-TL109	PLT4H-TL100	14.5 (368)			4.00 (102)			250	2500

*Order number of pieces required, in multiples of Bulk Package Quantity.

related products



Part Number	Used With Polypropylene Cable Ties	Description	Std. Pkg. Qty.
Tool Controlled Tension and Cut-Off Tools			
GTS-E, GS2B-E	Miniature, Intermediate, Standard	Tool controlled tension tools consistently provide flush tie cut-offs to speed installation.	1
GS4H-E, GTH-E, GS4EH-E	Standard, Light-Heavy		1



Installer Controlled Tension and Cut-Off Tools			
STS2	Miniature, Intermediate, Standard	Installer controlled tension tools are economical and ideal for low volume applications.	1
STH2	Standard, Light-Heavy		1
ST3EH	Light-Heavy		1



Pneumatic Tools			
PTS, PPTS	Miniature, Intermediate, Standard	Pneumatic, push button operation tools tension and cut-off excess tie in a fraction of a second.	1
PTH	Standard, Light-Heavy		1

WORLDWIDE SUBSIDIARIES AND SALES OFFICES

PANDUIT US/ CANADA
Phone: 800.777.3300

PANDUIT EUROPE LTD.
London, UK
cs-emea@panduit.com
Phone: 44.20.8601.7200

PANDUIT SINGAPORE PTE. LTD.
Republic of Singapore
cs-ap@panduit.com
Phone: 65.6305.7575

PANDUIT JAPAN
Tokyo, Japan
cs-japan@panduit.com
Phone: 81.3.6863.6000

PANDUIT LATIN AMERICA
Guadalajara, Mexico
cs-la@panduit.com
Phone: 52.33.3777.6000

PANDUIT AUSTRALIA PTY. LTD.
Victoria, Australia
cs-aus@panduit.com
Phone: 61.3.9794.9020

For a copy of Panduit product warranties, log on to www.panduit.com/warranty

PANDUIT®

Visit us at www.panduit.com
Contact Customer Service by email: cs@panduit.com
or by phone: 800.777.3300

©2017 Panduit Corp.
ALL RIGHTS RESERVED.
CTSP05--WW-ENG
6/2017