



**PAINTER'S TOUCH®  
2X ULTRA COVER ENAMEL SPRAYS**

**DESCRIPTION AND USES**

Rust-Oleum® Painter's Touch® 2X Ultra Cover contains technology that provides twice the coverage on wood, metal, most plastic, wicker and more when compared to other matching colors of Rust-Oleum general purpose paints: Painter's Touch, SPRAY N GO, Quick Color and Touch 'n tone. It covers surfaces with less spray passes, allowing projects to be completed faster and easier. Any angle spray feature allows you to spray in any direction, even upside down. Fast Drying.

**TIP:** Some plastics made of polyethylene such as plastic storage containers are manufactured in a way that may hinder maximum paint adhesion. Test paint in a hidden area first.

**PRODUCTS**

SKU	DESCRIPTION (Aerosol)
249089	Gloss Winter Gray
249090	Gloss White
249091	Gloss Warm Yellow
249092	Gloss Sun Yellow
249093	Gloss Spa Blue
249094	Gloss Sage Green
249095	Gloss Real Orange
249097	Gloss Purple
249098	Gloss Navy Blue
249099	Gloss Navajo White
249100	Gloss Meadow Green
249102	Gloss Kona Brown
249103	Gloss Khaki
249104	Gloss Key Lime
249110	Gloss Ivory
249111	Gloss Hunter Green
249113	Gloss Grape
249114	Gloss Deep Blue
249115	Gloss Dark Gray
249116	Gloss Colonial Red
249119	Gloss Candy Pink
249120	Gloss Brilliant Blue
249122	Gloss Black
249123	Gloss Berry Pink
249124	Gloss Apple Red
249125	Gloss Almond
249847	Gloss Chestnut
249862	Gloss Marigold
249863	Gloss Cranberry
267116	Gloss Seaside

**PRODUCTS (cont.)**

SKU	DESCRIPTION (Aerosol)
283189	Gloss Coral
283190	Gloss Ocean Mist
299910	Gloss Golden Sunset
314751	Gloss Spring Green
329198	Gloss Pink Peony
329200	Gloss Modern Mint
342060	Gloss Solstice Blue

**PRODUCT APPLICATION**

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not use on objects that may exceed 200°F (93°C) surface temperature. Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

**SURFACE PREPARATION**

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

**WARNING!** If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**PRIMING**

Use of Painter's Touch 2X Ultra Cover® primer provides superior adhesion and hiding and is especially recommended for bare wood and metal. The following primers are recommended

249058	White Primer
249086	Red Primer
249088	Gray Primer
249846	Flat Black Primer



# PAINTER'S TOUCH®

## 2X ULTRA COVER ENAMEL SPRAYS

### PRODUCT APPLICATION (cont.)

#### APPLICATION

Shake can vigorously for one minute after mixing ball begins to rattle. If mixing ball fails to rattle, DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2 or more light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**

#### DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 20 minutes, to handle in 1 hour, and is fully dry in 24 hours. Apply a second coat or clear coat within 1 hour or after 48 hours. Apply clear in 2-3 light coats a few minutes apart.

### PRODUCT APPLICATION (cont.)

**NOTE:** On plastic maximum paint adhesion and durability is achieved in 5-7 days.

#### CLEAN-UP

When finished spraying, wipe off tip before storing. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

#### CLOGGING

If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick pin or other object into the stem.

	<b>TECHNICAL DATA</b>	<b>PT2X-01</b>
	<b>PAINTER'S TOUCH®</b> <b>2X ULTRA COVER ENAMEL SPRAYS</b>	

**PHYSICAL PROPERTIES**

		2X ULTRA COVER ENAMEL SPRAYS
<b>Resin Type</b>		Acrylic Modified Alkyd
<b>Pigment Type</b>		Varies with color
<b>Solvents</b>		Acetone, n-Butyl Acetate, Naptha, Xylene
<b>MIR</b>		Max 0.95
<b>Fill Weight</b>		12 oz.
<b>Recommended Dry Film Thickness (DFT) per Coat</b>		1.0-2.0 mils (25-50μ)
<b>Practical Coverage at Recommended DFT (assume 15% material loss)</b>		8-12 sq.ft./can (0.74-1.11 m <sup>2</sup> /can)
<b>Dry Times at 70F (21°C) and 50% Relative Humidity</b>	<b>Touch</b>	20 minutes
	<b>Handle</b>	1 hour
	<b>Recoat</b>	Within 1 hour or after 48 hours
<b>Dry Heat Resistance</b>		200°F (93°C)
<b>Shelf Life</b>		5 years
<b>Flash Point</b>		-156°F (-104°C)
<b>Safety Information</b>		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.