



## KLEENGUARD\* A40 Liquid & Particle Protection Coveralls

### Product Information

Zipper Front	Code	Size	Quantity
	27151*	S	25
	44302	M	25
	44303	L	25
	44304	XL	25
	44305	2XL	25
	44306	3XL	25
	44307	4XL	25
	30922*	5XL	25
	30927*	6XL	25

Zipper Front, Elastic Wrists & Ankles	Code	Size	Quantity
	30905*	S	25
	44312	M	25
	44313	L	25
	44314	XL	25
	44315	2XL	25
	44316	3XL	25
	44317	4XL	25
	30904*	5XL	25
	27189*	6XL	25
	35630*	5XL/6XL combo	25

Zipper Front, Elastic Wrist, Ankles & Hood	Code	Size	Quantity
	30940*	S	25
	44322	M	25
	44323	L	25
	44324	XL	25
	44325	2XL	25
	44326	3XL	25
	44327	4XL	25
	27158	5XL	25
	30921*	6XL	25

Zipper Front, Elastic Wrists, Ankles, Hood & Boots	Code	Size	Quantity
	30939*	S	25
	44332	M	25
	44333	L	25
	44334	XL	25
	44335	2XL	25
	44336	3XL	25
	44337	4XL	25
	30907*	5XL	25
	30934*	6XL	25

\*Made-to-order Codes

### Workmanship Requirements

Coveralls shall be made in accordance with reasonable industry practice with respect to holes, tears, wrinkles, cleanliness, and foreign materials or dirt. For additional information: 1-888-346-4652 or [kimtech@kcc.com](mailto:kimtech@kcc.com)

Kimberly-Clark warrants that its products (1) comply with K-C's standard specifications as of the delivery date to K-C's authorized distributors/direct purchasers and are warranted for the following periods from end user's date of purchase (verified by valid sales receipt) (a) five years for Balder Technology auto darkening filters; (b) two years for all other auto darkening filters; and (c) one year for powered air purifying respirators; (2) comply with all K-C labeling representations; and (3) are manufactured in compliance with all applicable federal, state, and local laws in effect at the time and place of manufacture of the products. THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. K-C is not liable for any kind of special, incidental, or consequential damages. K-C's liability for breach of contract, tort or other cause of action shall not exceed the product purchase price. Purchasers and users are deemed to have accepted the above warranty and limitation of liability, and cannot change the terms by verbal agreement or by any writing not signed by K-C. To the extent required by applicable law, K-C does not limit its liability for death/injury resulting from K-C's negligence.

©/™Trademarks of Kimberly-Clark Worldwide, Inc. or its affiliates. Marques déposées de Kimberly-Clark Worldwide, Inc. ou de ses filiales. © 2013 KCWW.

### Fabric Properties

Physical Properties	Results	Test Methods
Tensile Strength (MD)	30.6 lbs	ASTM D5034
Tensile Strength (CD)	21.4 lbs	ASTM D5034
Trapezoidal Tear (MD)	11.0 lbs	INDA IST 100.2
Trapezoidal Tear (CD)	7.2 lbs	INDA IST 100.2
Elongation (MD)	72%	ASTM D5034
Elongation (CD)	89%	ASTM D5034
Lint - # of particles >0.5 microns	761	INDA 1601-92
Flammability	Class 1	CPSC 1610
Barrier Properties	Results	Test Methods
Hydrohead	187 cm	AATCC 127-1998
Particle Holdout (0.3-0.5 microns)	100%	Independent Lab
Blood Penetration	Pass	ASTM F1670

### Features

Microporous film laminate
Non-latex polyisoprene elastic
No silicone
No BHT preservative
NFPA 99 Compliant antistatic material
Meets ANSI/ISEA 101-1996 sizing standards
Passes ASTM F1670 testing for penetration of blood & bodily fluids
Serged seams